

Cordenka[®] Growth 500 GA1

Product Description

Compostable rayon based cellulose fiber twine
for green house applications

Properties

Property	Unit	Typical Value
Linear denisty	dtex	14.000
Breaking force	N	500
Elongation at break	%	13,0
Yield	m / kg	700

All tests performed at cord material conditioned in standard climate (65% rel. humidity, 20 °C)
with a cord moisture content of approx. 13%.

Development type Status 09/2019

Technical data subject to change

Manufacturer:

Cordenka GmbH & Co. KG
Industriecenter Obernburg
63784 Obernburg, Germany
www.cordenka.com

Cordenka[®] Growth Sales Contact:

Ecolander UK LTD
12A, Lye Valley Industrial Estate
Stourbridge, West Midlands, DY9 8HX
United Kingdom
www.Ecolander.co.uk
E-Mail: paul.willetts@ecolander.co.uk
Phone: +44 1384 596 386

CORDENKA[®]

Premium Rayon Reinforcement

The data given in this document constitutes average values. The data and information given are based on our knowledge and experience to date and are not intended for use in component design, nor do they in any way constitute an implied warranty of material properties. Evaluation of the material's suitability for any specific intended application is the sole responsibility of the processor. This document supersedes all previous issues.